

### Analysis of Bitumen MC30

Properties	Min.	Max.	Test Method
Kinemalic 1 Viscosity at 60°C, EST	30	60	ASTM D2170
Flash Point (Tag Open-Cup), °C	38	–	ASTM D1310
Distillate test 2:	–	–	–
<b>Distillate, Percent by Volume of Total 360°C</b>			
To 190°C	–	15	ASTM D402
To 225°C	20	60	ASTM D402
To 260°C	50	90	ASTM D402
To 316°C	80	90	ASTM D402
<b>Residue From Distillation to 360°C:</b>			
Test on Residue From Distillation Penetration at 25°C, 100g, 5 Sec.	50	–	–
Ductility 3 at 25°C, cm	120	250	ASTM D402/ASTM D113
Solubility in Trichloroethylene, Percent Mass	100	–	ASTM D402 / ASTM D2024
Water, Percent Volume	–	0.2	ASTM D95

### Analysis of Bitumen MC70

Properties	Min.	Max.	Test Method
Kinematic 1 Viscosity at 60°C, EST	70	140	ASTM D2170
Flash Point (Tag Open-Cup), °C	38	–	ASTM D1310
Distillate test 2:	–	–	–
<b>Distillate, Percent by Volume of Total 360°C</b>			
To 190°C	–	15	ASTM D402
To 225°C	20	60	ASTM D402
To 260°C	65	90	ASTM D402
To 316°C	55	_ S	ASTM D402
<b>Residue From Distillation to 360°C:</b>			
Test on Residue From Distillation Penetration at 25°C, 100g, 5 Sec.	50	–	–
Ductility 3 at 25°C, cm	120	250	ASTM D402/ASTM D113
Solubility in Trichloroethylene, Percent Mass	100	–	ASTM D402 / ASTM D2024
Water, Percent Volume	–	0.2	ASTM D95

### Analysis of Bitumen MC250

Properties	Min.	Max.	Test Method
Kinematic 1 Viscosity at 60°C, EST	250	500	ASTM D2170
Flash Point (Tag Open-Cup), °C	66	–	ASTM D1310
Distillate test 2:	–	–	–
<b>Distillate, Percent by Volume of Total 360°C</b>			
To 190°C	–	10	ASTM D402
To 225°C	15	55	ASTM D402
To 260°C	60	87	ASTM D402
To 316°C	67	–	ASTM D402
<b>Residue From Distillation to 360°C:</b>			
Test on Residue From Distillation Penetration at 25°C, 100g, 5 Sec.	30	120	–
Ductility 3 at 25°C, cm	120	250	ASTM D402/ASTM D113
Solubility in Trichloroethylene, Percent Mass	100	–	ASTM D402 / ASTM D2024
Water, Percent Volume	–	0.2	ASTM D95

### Analysis of Bitumen MC800

Properties	Min.	Max.	Test Method
Kinematic 1 Viscosity at 60°C, EST	800	1600	ASTM D2170
Flash Point (Tag Open-Cup), °C	66	–	ASTM D1310
Distillate test 2:	–	–	–
<b>Distillate, Percent by Volume of Total 360°C</b>			
To 190°C	–	15	ASTM D402
To 225°C	20	60	ASTM D402
To 260°C	50	90	ASTM D402
To 316°C	80	90	ASTM D402
<b>Residue From Distillation to 360°C:</b>			
Test on Residue From Distillation Penetration at 25°C, 100g, 5 Sec.	50	–	–
Ductility 3 at 25°C, cm	120	250	ASTM D402/ASTM D113
Solubility in Trichloroethylene, Percent Mass	100	–	ASTM D402 / ASTM D2024
Water, Percent Volume	–	0.2	ASTM D95

<b>Analysis of Bitumen MC3000</b>			
<b>Properties</b>	<b>Min.</b>	<b>Max.</b>	<b>Test Method</b>
Kinemalic 1 Viscosity at 60°C, EST	3000	6000	ASTM D2170
Flash Point (Tag Open-Cup), °C	66	–	ASTM D1310
Distillate test 2:	–	–	–
<b>Distillate, Percent by Volume of Total 360°C</b>			
To 190°C	–	–	ASTM D402
To 225°C	–	–	ASTM D402
To 260°C	–	15	ASTM D402
To 316°C	80	–	ASTM D402
<b>Residue From Distillation to 360°C:</b>			
Test on Residue From Distillation Penetration at 25°C, 100g, 5 Sec.	80	–	–
Ductility 3 at 25°C, cm	120	250	ASTM D402/ASTM D113
Solubility in Trichloroethylene, Percent Mass	100	–	ASTM D402 / ASTM D2024
Water, Percent Volume	–	0.2	ASTM D95